

Verso 3 (end 31.12.2024)		Technical info	
<b>Composition</b>		Fibreglass 36% - PVC 64%	
<b>Openness factor</b>	NBN EN 410	3.00%	
<b>Weight</b>	NF EN 12127	470.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.55 mm	
<b>Density</b>	ISO 7211/2	WARP 24.00 yarn/cm	WEFT 23.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Roll length</b>		30 m	
<b>Cleaning</b>		With soapy water	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	B-s2,d0	
└ Germany	DIN 4102	B2	
<b>Tear strength</b>	ISO 4674-1 methode 2		
└ Original		WARP 5.90 daN	WEFT 4.60 daN
└ After climatic chamber -30°C		WARP 6.30 daN	WEFT 5.50 daN
└ After climatic chamber +70°C		WARP 6.00 daN	WEFT 4.70 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 2.70 %	WEFT 3.60 %
└ After color fastness to artificial light		WARP 2.90 %	WEFT 3.30 %
└ After climatic chamber -30°C		WARP 2.75 %	WEFT 2.40 %
└ After climatic chamber +70°C		WARP 2.30 %	WEFT 2.35 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 155.00 daN/5cm	WEFT 180.00 daN/5cm
└ After color fastness to artificial light		WARP 160.00 daN/5cm	WEFT 170.00 daN/5cm
└ After climatic chamber -30°C		WARP 150.00 daN/5cm	WEFT 110.00 daN/5cm
└ After climatic chamber +70°C		WARP 100.00 daN/5cm	WEFT 100.00 daN/5cm